

<b>Quality</b>	<b>X5CrNiMo17-12-2</b>	<b>Austenitic</b>	<i>Technical card</i>
Number	<b>1.4401</b>	<b>Stainless Steel</b>	<i>Lucefina Group</i>

### Chemical composition

C%	Si%	Mn%	P%	S% <sup>a)</sup>	Cr%	Ni%	N%	Mo%	
max	max	max	max	max			max		
0,07	1,00	2,00	0,045	0,015	16,5-18,5	10,0-13,0	0,11	2,0-2,5	EN 10088-1: 2005
± 0.01	+ 0.05	+ 0.04	+ 0.005	+ 0.003	± 0.2	± 0.15	± 0.01	± 0.1	

Product deviation are allowed

<sup>a)</sup> for improving machinability, it is allowed a controlled sulphur content of 0,015 % - 0,030 %; for polishability, it is suggested a controlled sulphur content of max 0,015 %

### Temperature °C

Melting range	Hot-forming	Solution annealing (Solubilization)	Stabilizing	Soft annealing	MMA welding – AWS electrodes
1400-1380	1200-900	1100-1050 water	unnecessary	not suitable	<i>pre-heating</i> not required <i>post welding</i> slow cooling
Sensitization	Quenching	Tempering	<i>joint with steel</i>		
sensitization test at 800-450	not suitable	not suitable	carbon	CrMo alloyed	stainless
			E309-E308	E309-E308	E308
			<i>cosmetic welding</i> E 316 or E 16-8-2		

### Mechanical properties

**Hot-formed** EN 10088-3: 2005 in conditions 1C, 1E, 1D, 1X, 1G, 2D

size mm		Testing at room temperature						
from	to	R	Rp 0.2	A% (L)	A% (T)	Kv +20 °C (L)	Kv +20 °C (T)	HB <sup>a)</sup>
		N/mm <sup>2</sup>	N/mm <sup>2</sup> min	min		J min	J min	max
	160	500-700	200	40		100		215 +AT solubilization
160	250	500-700	200		30		60	215 +AT solubilization

<sup>a)</sup> for information only

(L) = longitudinal (T) = transversal

**Cold processed** EN 10088-3: 2005 in conditions 2H, 2B, 2G, 2P

size mm		Testing at room temperature						
from	to	R	Rp 0.2	A% (L)	A% (T)	Kv +20 °C (L)	Kv +20 °C (T)	
		N/mm <sup>2</sup>	N/mm <sup>2</sup> min	min	min	J min	J min	
	10 <sup>b)</sup>	600-950	400	25				
10	16	580-950	380	25				+AT solubilization
16	40	500-850	200	30		100		
40	63	500-850	200	30		100		
63	160	500-700	200	40		100		
160	250	500-700	200		30		60	

<sup>b)</sup> in the range of 1 mm ≤ d < 5 mm, values are valid only for rounds – the mechanical properties of non round bars of < 5 mm of thickness have to be agreed at the time of request and order

(L) = longitudinal (T) = transversal

**Forged** +AT solubilization

size mm		Testing at room temperature						
from	to	R	Rp 0.2	A%	A%	Kv +20 °C	Kv +20 °C	Kv -196 °C
		N/mm <sup>2</sup>	N/mm <sup>2</sup> min	min (L)	min (T)	J min (L)	J min (T)	J min (T)
	250	500-700	200		30	100	60	
	250	510-710	205	45	35	100	60	60
								EN 10250-4: 2001
								EN 10222-5: 2001

**Work-hardened by cold-drawing** EN 10088-3: 2005 in condition 2H (es. +AT+C)

size mm		Testing at room temperature			
from	to	R	Rp 0.2	A%	
		N/mm <sup>2</sup>	N/mm <sup>2</sup> min	min	
	35	700-850	350	20	+AT+C700 cold-drawn material
	25	800-1000	500	12	+AT+C800 cold-drawn material

**Transition curve** determined by Kv impacts. Material solubilized at 1050 °C

Average	J	198	206	218	225	238	245	250
Test at	°C	-160	-120	-80	-40	0	+40	+80

**Approximate mechanical properties at low temperatures.** Material solubilized at 1080 °C

<b>R</b>	N/mm <sup>2</sup>	580	820	1270	1440
<b>Rp 0.2</b>	N/mm <sup>2</sup>	245	330	520	580
<b>A</b>	%	55	50	45	40
Test at	°C	<b>+24</b>	<b>-74</b>	<b>-196</b>	<b>-254</b>

Effect of cold-working (hot-rolled +AT+C). Approximate values

R	N/mm <sup>2</sup>	550	660	800	1000	1110
R <sub>p 0.2</sub>	N/mm <sup>2</sup>	260	510	640	790	840
A	%	50	22	14	13	10
Reduction	%	0	10	20	30	40

Minimum yield stress and tensile strength values at high temperatures on material +AT, EN 10088-3: 2005/EN 10269: 2001

R <sub>p 0.2</sub>	N/mm <sup>2</sup>	175	158	145	135	127	120	115	112	110	108
R	N/mm <sup>2</sup>	460	440	420	415	410	410	410	405	390	375
Test at	°C	100	150	200	250	300	350	400	450	500	550

Thermal expansion	10 <sup>-6</sup> · K <sup>-1</sup>	12.8	13.3	14.1	▶	16.0	16.5	17.0	17.5	18.8	20.2
Modulus of elasticity	longitudinal GPa					200	194	186	179	172	127
Modulus of elasticity	tangential GPa					78					
Poisson number	ν					0.256	0.280				
Electrical resistivity	Ω · mm <sup>2</sup> /m	0.58		0.66	0.75		0.86		0.97	1.07	1.15
Electrical conductivity	Siemens · m/mm <sup>2</sup>				1.33						
Specific heat	J/(Kg · K)				500		510		550	585	630
Density	Kg/dm <sup>3</sup>				7.98						
Thermal conductivity	W/(m · K)				15.0		17.5	19.9			25.1
Relative magnetic permeability	μ <sub>r</sub>				1.02						
Temperature	°C	-184	-128	-74	20	100	200	300	400	600	800

The symbol ▶ indicates between 20 °C and 100 °C, 20 °C and 200 °C .....

Corrosion resistance	Atmospheric		Chemical			x halides, sulfuric acid, phosphoric, organic and formic acids
Fresh water	<i>industrial</i>	<i>marine</i>	<i>medium</i>	<i>oxidizing</i>	<i>reducing</i>	
x	x	x	x	x	x	
Magnetic	no					
Machinability	low					
Hardening	cold-drawn and other cold plastic deformations					
Service temperature in air	continuous service up to 850 °C; intermittent service up to 800 °C					

Europe	USA	USA	China	Russia	Japan	India	Rep. of Korea
EN	UNS	ASTM	GB	GOST	JIS	IS	KS
X5CrNiMo17-12-2	S31600	316	0Cr17Ni12Mo2	08Ch17N13M2	SUS 316	X04Cr17Ni12Mo2	STS 316

Approximate diagram of cold-drawn hardening

